

Summer 6-24-2014

Stress and crack monitoring during plasma spraying of TBC

Seiji Kuroda

National Institute for Materials Science

Xiancheng Zhang

East China University of Science and Technology

Makoto Watanabe

National Institute for Materials Science

Kaita Ito

The University of Tokyo

Manabu Enoki

The University of Tokyo

Follow this and additional works at: http://dc.engconfintl.org/thermal_barrier_iv



Part of the [Materials Science and Engineering Commons](#)

Recommended Citation

Seiji Kuroda, Xiancheng Zhang, Makoto Watanabe, Kaita Ito, and Manabu Enoki, "Stress and crack monitoring during plasma spraying of TBC" in "Thermal Barrier Coatings IV", U. Schulz, German Aerospace Center; M. Maloney, Pratt & Whitney; R. Darolia, GE Aviation (retired) Eds, ECI Symposium Series, (2015). http://dc.engconfintl.org/thermal_barrier_iv/16

This Conference Proceeding is brought to you for free and open access by the Proceedings at ECI Digital Archives. It has been accepted for inclusion in Thermal Barrier Coatings IV by an authorized administrator of ECI Digital Archives. For more information, please contact franco@bepress.com.

STRESS AND CRACK MONITORING DURING PLASMA SPRAYING OF TBC

Seiji Kuroda, National Institute for Materials Science (NIMS)
 KURODA.Seiji@nims.go.jp
 Xiancheng Zhang, East China University of Science and Technology
 Makoto Watanabe, NIMS
 Kaita Ito and Manabu Enoki, The University of Tokyo

Key Words: Curvature, residual stress, segmentation cracking, process monitoring, acoustic emission method.

Two types of process monitoring techniques are compared and discussed in this presentation. The first one is in-situ curvature monitoring, by which it was possible to evaluate the stress evolution during plasma spraying and separately identify the sources of stresses, i.e., the quenching stress and thermal stress as shown in Fig.1 (a). By changing the spraying parameters, it was possible to prepare specimens at largely different deposition temperatures, which resulted in significantly different levels of residual stresses. Also, it was found that the mechanical properties of the obtained YSZ coatings such as the elastic modulus are strongly dependent on the deposition temperature as shown in Fig.1 (b). Four-point bending test was conducted to these coatings, which clearly showed that the compressive residual stress effectively offset the applied tensile stress to initiate cracking in the YSZ coatings. Another method is based on acoustic emission (AE). Non-contacting laser AE sensors as shown in Fig.2 were used to detect cracking in YSZ coatings during spraying. Due to the intensive noise from the plasma spraying environment, extensive signal processing techniques have been developed to eliminate the noise in the frequency and time domains by using digital filtering and multi-threshold techniques. The obtained results so far indicate that the through thickness temperature gradient during spraying plays a major role in the formation of deep vertically segmentation cracks.

References

- Zhang, X., M. Watanabe, and S. Kuroda, Effects of residual stress on the mechanical properties of plasma-sprayed thermal barrier coatings, *Engineering Fracture Mechanics*, 110 (2013) 314–327.
- Zhang, X., M. Watanabe, and S. Kuroda, Effects of processing conditions on the mechanical properties and deformation behaviors of plasma-sprayed thermal barrier coatings: Evaluation of residual stresses and mechanical properties of thermal barrier coatings on the basis of in situ curvature measurement under a wide range of spray parameters, *Acta Materialia*, 61 (2013) 1037-1047.
- Ito, K., H. Kuriki, M. Watanabe, S. Kuroda, and M. Enoki, Detection of AE Events due to Cracks in TBC during Spraying Process. *Materials Transactions*, 53(4) (2012) 671-675.




Fig.1 (a) Residual stresses in and (b) elastic modulus of plasma sprayed TBC formed at different deposition temperatures^(1,2).




Fig.2 Schematic of laser AE measurement during plasma spraying⁽³⁾.