

Fall 11-11-2015

Using polymer brushes to tune the structure-plasmonic relationship in polymer nanocomposites containing nanorods

Russell Composto
University of Pennsylvania

Follow this and additional works at: http://dc.engconfintl.org/composites_all



Part of the [Materials Science and Engineering Commons](#)

Recommended Citation

Russell Composto, "Using polymer brushes to tune the structure-plasmonic relationship in polymer nanocomposites containing nanorods" in "Composites at Lake Louise (CALL 2015)", Dr. Jim Smay, Oklahoma State University, USA Eds, ECI Symposium Series, (2016). http://dc.engconfintl.org/composites_all/94

This Conference Proceeding is brought to you for free and open access by the Proceedings at ECI Digital Archives. It has been accepted for inclusion in Composites at Lake Louise (CALL 2015) by an authorized administrator of ECI Digital Archives. For more information, please contact franco@bepress.com.

USING POLYMER BRUSHES TO TUNE THE STRUCTURE-PLASMONIC RELATIONSHIP IN POLYMER NANOCOMPOSITES CONTAINING NANORODS

Russell J. Composto
Materials Science and Engineering, and
The Laboratory for Research on the Structure of Matter,
University of Pennsylvania
Philadelphia, PA 19104

The thermodynamic factors that affect the dispersion of polymer-brush grafted gold nanorods (NRs) added to polymer matrix films have been studied by experiment and theory. When the brush (degree of polymerization N) and matrix (degree of polymerization P) have a favorable interaction (enthalpy driven), NRs uniformly disperse in the matrix, independent of P/N . When the brush and matrix are chemically similar, NRs randomly disperse for $P/N < 2$ (i.e., wet brush), but align side-by-side for $P/N > 2$. UV-visible spectroscopy is used to investigate the structure-optical property relationship as function of P/N . For $P/N > 2$, self-consistent field theory (SCFT) and density functional theory (DFT) indicate that NR aggregation correlates with rod-rod interactions greater than $5kT$. As NR aspect ratio (AR) increases, dry and wet brush behavior is observed for ARs from 2.5 to 6.3. For $P/N < 2$, long NRs exhibit much longer range local order than short NRs and corresponding strong blue shift in the longitudinal surface plasmon resonance (LSPR). Chemically mixed brushes on NR surfaces provide another means to tune NR dispersion. To induce end-to-end linking, Au NRs are selectively functionalized with dithiols and peptides to create permanent and revisable linking as well as a red shift in the LSPR.