

## DEPOLYMERIZATION OF FRACTIONATED WOOD BY HYDROTHERMAL LIQUEFACTION

Felipe BUENDIA-KANDIA, Reactions and Chemical Engineering Laboratory (LRGP), CNRS, University of Lorraine, France

andres-felipe.buendia-kandia@univ-lorraine.fr

Nicolas BROSSE, Wood Materials Research Laboratory (LERMAB), Sciences and Technologies Faculty, University of Lorraine, France

Guillain MAUVIEL, Reactions and Chemical Engineering Laboratory (LRGP), CNRS, University of Lorraine, France

Anthony DUFOUR, Reactions and Chemical Engineering Laboratory (LRGP), CNRS, University of Lorraine, France

Key Words: Biomass, cellulose, fractionation, organosolv, depolymerization, hydrothermal, liquefaction

Direct thermochemical conversion of lignocellulosic biomass produces a mixture of compounds that have to be separated to produce purified building blocks. Moreover, lignin derived products have a detrimental effect on further biological conversion processes, such as fermentation. For all these reasons, it is important to develop an integrated approach for a better fractionation and valorisation of macromolecules (carbohydrates and lignin) in bio-refineries.

In this work, wood is fractionated producing cellulose-rich pulps that are converted by hydrothermal liquefaction into fermentable sugars (*Figure 1*). For this purpose, beech has been delignified either by ethanol organosolv or by sodium chlorite/acetic acid (SC/AA) treatment, obtaining delignification yields of 50 and 91 wt. % respectively. The recovered pulps were then submitted to liquefaction in hot-compressed water (HCW). Three temperatures were studied: 180, 200 and 220°C during 2 h. The same experiments were conducted on untreated beech and model cellulose (Avicel PH-101). Product yields and total carbohydrates were determined. The liquefaction products, i.e. solid residue, water soluble compounds and permanent gas, were analyzed respectively by X-ray diffraction (XRD), high performance anion-exchange chromatography with pulsed amperometric detector (HPAEC-PAD) and gas chromatography (GC). SC/AA treatment allowed a high recovery of hemicelluloses and for this reason, xylose content was significantly higher for the SC/AA pulp. The maximum yields of total carbohydrates, i.e. 13.7 and 36.8 wt.% from the organosolv and SC/AA pulp respectively, were found when the liquefaction temperature was 220°C.




Figure 1 - Schematic representation of the hydrothermal conversion of the wood pulps. Typical yields of the most representatives compounds are indicated.